

# MVQ diet

Methyl-vinyl-silicone-rubber

Standard colour: blue, similar RAL 5024

- Food-compliant MVQ
- Resistant to mineral oil, HFD-U and cold water
- Applicable for Rod and Piston Seals, Wiper Seals and Static Seals

Properties	Value	Unit	DIN Standard
Hardness	84 ± 5	Shore A	DIN 53505
Density	1,503	g/cm <sup>3</sup>	DIN EN ISO 1183-1
Compression set 22°C/72h		%	DIN ISO 815-1
Compression set 70°C/24h		%	DIN ISO 815-1
Compression set 175°C/24h	33,7	%	DIN ISO 815-1
Elongation at break	192	%	DIN 53504
Tensile strength	6,4	MPa	DIN 53504
100% modulus	5,3	MPa	DIN 53504
Rebound resilience	51	%	DIN 53512
Abrasion	108	mm <sup>3</sup>	DIN 53516
Tear strength	10,2	N/mm	DIN 53515
min. service temperature	- 50	°C	
max. service temperature	+210	°C	

All above stated data results from random tests which were taken from the ongoing production. All data was established based on standard test-products according to ISO, DIN and ASTM standards and can basically not be carried over to the completed seal.

Our applied technical advice, either oral, written or through tests is given according to our best knowledge. However, this information is to be considered as non-obligatory instruction, also in terms of any protective rights of a third party, and does not exempt you from testing our product in reference to its suitability for the intended process and purpose. Utilisation, application and processing of the products occur entirely outside of our control and are therefore exclusively your responsibility. However, should a case of liability come into question, it will be limited to all damages in the value of the product which we delivered and you used. By all means, we do warrant the impeccable quality of our products in accordance with our general sales and delivery conditions.